

Zink coating standaard gegalvaniseerd draad

| DIAM. | Klasse A g/m ² | Klasse B g/m ² | Klasse C g/m ² | Klasse D g/m ² |
|------------|------------------------------|------------------------------|------------------------------|------------------------------|
| 0.20-0.24 | 30 | 20 | 20 | 15 |
| 0.25-0.31 | 45 | 30 | 25 | 15 |
| 0.32-0.39 | 60 | 30 | 25 | 15 |
| 0.40-0.49 | 85 | 40 | 30 | 15 |
| 0.50-0.59 | 100 | 50 | 35 | 20 |
| 0.60-0.69 | 115 | 60 | 40 | 20 |
| 0.70-0.79 | 130 | 60 | 45 | 20 |
| 0.80-0.89 | 145 | 70 | 50 | 20 |
| 0.90-0.99 | 155 | 70 | 55 | 25 |
| 1.00-1.19 | 165 | 80 | 60 | 25 |
| 1.20-1.39 | 180 | 90 | 65 | 25 |
| 1.40-1.64 | 195 | 100 | 70 | 30 |
| 1.65-1.84 | 205 | 100 | 75 | 30 |
| 1.85-2.14 | 215 | 115 | 80 | 40 |
| 2.15-2.49 | 230 | 125 | 85 | 45 |
| 2.50-2.79 | 245 | 125 | 95 | 45 |
| 2.80-3.19 | 255 | 135 | 100 | 50 |
| 3.20-3.79 | 265 | 135 | 105 | 60 |
| 3.80-4.39 | 275 | 135 | 110 | 60 |
| 4.40-5.19 | 280 | 150 | 110 | 70 |
| 5.20-8.19 | 290 | | 110 | 80 |
| 8.20-10.00 | 300 | | 110 | 80 |