

Zink Beschichtung Standard Galvanisierter Draht

DIAM.	Klasse A g/m ²	Klasse B g/m ²	Klasse C g/m ²	Klasse D g/m ²
0.20-0.24	30	20	20	15
0.25-0.31	45	30	25	15
0.32-0.39	60	30	25	15
0.40-0.49	85	40	30	15
0.50-0.59	100	50	35	20
0.60-0.69	115	60	40	20
0.70-0.79	130	60	45	20
0.80-0.89	145	70	50	20
0.90-0.99	155	70	55	25
1.00-1.19	165	80	60	25
1.20-1.39	180	90	65	25
1.40-1.64	195	100	70	30
1.65-1.84	205	100	75	30
1.85-2.14	215	115	80	40
2.15-2.49	230	125	85	45
2.50-2.79	245	125	95	45
2.80-3.19	255	135	100	50
3.20-3.79	265	135	105	60
3.80-4.39	275	135	110	60
4.40-5.19	280	150	110	70
5.20-8.19	290		110	80
8.20-10.00	300		110	80